

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b> <b>C08G 65/32, A61K 49/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 94/09056</b> <b>(43) International Publication Date:</b> 28 April 1994 (28.04.94)
<b>(21) International Application Number:</b> PCT/US93/09587 <b>(22) International Filing Date:</b> 7 October 1993 (07.10.93)  <b>(30) Priority data:</b> 961,146 14 October 1992 (14.10.92) US  <b>(71) Applicant:</b> STERLING WINTHROP INC. [US/US]; 90 Park Avenue, New York, NY 10016 (US).  <b>(72) Inventors:</b> SNOW, Robert, A. ; 118 Cratin Lane, West Chester, PA 19380 (US). LADD, David, L. ; 1375 Thomas Road, Wayne, PA 19087 (US). TONER, John, L. ; 109 Brookhollow Drive, Downingtown, PA 19355 (US).  <b>(74) Agent:</b> DAVIS, William, J.; 343 State Street, Rochester, NY 14650-2201 (US).		<b>(81) Designated States:</b> AU, CA, CZ, FI, HU, JP, KR, NO, RU, SK, UA, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> CHELATING POLYMERS  <b>(57) Abstract</b>  In accordance with this invention, there is provided a polymer comprising units comprising the residue of a chelating agent linked to a poly(alkylene oxide) moiety, and a method for the preparation thereof. The polymer is particularly useful in therapeutic and diagnostic imaging compositions and as an antistatic agent.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TG	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

## CHELATING POLYMERS

## CROSS REFERENCE TO RELATED APPLICATIONS

5

Reference is hereby made to commonly assigned  
copending U.S. Patent Application Serial No. -----  
entitled MR IMAGING COMPOSITIONS AND METHODS and U.S.  
Patent Application Serial No. ----- entitled THERAPEUTIC  
10 AND DIAGNOSTIC IMAGING COMPOSITIONS AND METHODS filed  
concurrently herewith.

## FIELD OF THE INVENTION

15

This invention relates to novel chelating  
polymers containing poly(alkylene oxide) moieties and  
methods for the preparation thereof.

20

## BACKGROUND OF THE INVENTION

20

Poly(ethylene glycols) (PEGs) and derivatives  
thereof are finding a rapidly expanding range of  
chemical, biomedical, and industrial applications  
resulting from their low cost and useful properties,  
25 such as solubility in aqueous and organic solvents,  
metal complexing ability, biological compatibility and  
ease of site specific chemical modification. Such  
polymers have been employed, for example, as matrices  
for liquid phase peptide synthesis, ligands for water  
30 soluble transition metal complexes and drug carriers.

With the development of new application areas,  
there is a growing demand for new and improved PEG  
derivatives which can be tailored to meet user  
requirements.

35

Inada et al, U.S. Patent No. 4,814,098  
disclose a conjugate comprising a magnetic material and  
a physiologically active substance bound to each other  
through a poly(ethylene glycol) derivative.

Mutter, Tetrahedron Letters, 31, 2839-2842 (1978) describes a procedure to convert the terminal hydroxyl groups of PEG to reactive primary amino groups and the preparation of a number of reagents bound to PEG-NH<sub>2</sub>. However, there is no suggestion of a polymer containing units comprising a poly(alkylene oxide) moiety linked to a chelating group.

Harris et al, J. Polymer. Science, 22, 341-352 (1984) describe various PEG derivatives including PEG-amine. However, there is no suggestion of a polymer containing units comprising a poly(alkylene oxide) moiety linked to a chelating group.


European Patent Application 200,467 describes superoxide dismutase chemically modified with poly(alkylene oxide) which can be used to remove toxic substances derived from oxygen from the blood circulation. The modified superoxide dismutase has a molecular structure in which both ends of a poly(alkylene oxide) molecule are attached to the superoxide dismutase.

#### SUMMARY OF THE INVENTION

We have discovered that novel chelating polymers which find particular utility in therapeutic and diagnostic imaging compositions can be prepared by contacting reactive poly(alkylene oxides) with chelating agents or precursors thereof containing reactive functionality.

More particularly, in accordance with this invention, there is provided a polymer comprising units comprising the residue of a chelating agent linked to a poly(alkylene oxide) moiety. The polymer preferably comprises units having the structure:

I.



wherein:

5        Z is the residue of a chelating agent;

         Q is a poly(alkylene oxide) moiety;

         L and L<sub>1</sub> independently represent a chemical bond or  
a linking group;

         M<sup>(+a)</sup> is one or more cations having a total charge  
10    of +a;

         E<sup>(b)</sup> is one or more counterions having a total  
charge of b;

         w is 0 or 1;

         r is 0 or 1;

15        d is the total charge on the linked residue of the  
chelating agent; and

         a = d+b.

         In another aspect, this invention provides a  
method of preparing the above-described polymer which  
20    comprises contacting a reactive poly(alkylene oxide)  
species with a chelating agent or precursor thereof  
containing reactive functionality in a non-reactive  
solvent and optionally contacting said polymer with a  
source of metal ions.

25        It is an advantageous feature of this  
invention that novel polymers are provided having  
particular utility in therapeutic and diagnostic imaging  
compositions.

         It is another advantageous feature that a wide  
30    variety of polymers of specified composition, size and  
molecular weight can be prepared in accordance with this  
invention.

Other advantageous features of this invention will become readily apparent upon reference to the following descriptions of preferred embodiments.

5 DESCRIPTION OF PREFERRED EMBODIMENTS

The chelating polymer of this invention finds utility as a scavenger for metal ions, as an antistatic agent for use in photographic and magnetic recording  
10 elements, and as an additive for paints, coatings and adhesives. In addition, certain polymers of this invention find particular utility as contrast agents for use in magnetic resonance (MR) diagnostic imaging compositions and methods and as therapeutic agents as  
15 described further in the above-referenced related applications.

The polymer of this invention comprises units containing the residue of a chelating agent linked to a poly(alkylene oxide) moiety in the backbone of the  
20 polymer. The polymer can comprise from 2 to 1000 or more, preferably 3 to 1000 of the above-described units. In preferred embodiments, the above-described units are recurring units.

In formula I above, Q represents a linear or  
25 branched poly(alkylene oxide) moiety. Exemplary poly(alkylene oxide) moieties include poly(ethylene oxides), poly(propylene oxides) and poly(butylene oxides). Preferred poly(alkylene oxides) include poly(ethylene oxides) (PEO), poly(propylene oxides)  
30 (PPO) and random and block copolymers of PEO and PPO. PEO containing polymers are particularly preferred when it is desired for the final polymer to possess solubility in water. It is also contemplated that the poly(alkylene oxide) moiety can comprise glycerol  
35 poly(alkylene oxide) triethers, polyglycidols, linear, block and graft copolymers of alkylene oxides with compatible comonomers such as poly(ethyleneimine-co-ethylene oxide), and grafted block copolymers such as

poly(methyl vinyl ether-co-ethylene oxide). The poly(alkylene oxide) moieties have an average molecular weight in the range from about 100-200,000, preferably 250-100,000 and more preferably 250-20,000 daltons.


- 5 Preferred moieties can be derived from poly(alkylene oxide) moieties which are commercially available in the corresponding diol form and/or can be prepared by techniques well known to those skilled in the art. A particularly preferred class of PEO moieties derived  
10 from PEGs can be represented by the structure  $-(CH_2CH_2O)_mCH_2CH_2-$  wherein m is 1 to 5,000, preferably 1 to 2500, and more preferably 1 to 500.

The polymer of the invention can comprise the residue of one or more of a wide variety of chelating agents. As  
15 is well known, a chelating agent is a compound containing donor atoms that can combine by coordinate bonding with a cation to form a cyclic structure called a chelation complex or chelate. This class of compounds is described in the Kirk-Othmer Encyclopedia of Chemical Technology;  
20 Vol. 5, 339-368.


- The residues of suitable chelating agents can be selected from polyphosphates, such as sodium tripolyphosphate and hexametaphosphoric acid;  
aminocarboxylic acids, such as  
25 ethylenediaminetetraacetic acid, N-(2-hydroxyethyl)ethylenediaminetriacetic acid, nitrilotriacetic acid, N,N-di(2-hydroxyethyl)glycine, ethylenebis(hydroxyphenylglycine) and diethylenetriamine pentacetic acid;  
30 1,3-diketones, such as acetylacetone, trifluoroacetylacetone, and thenoyltrifluoroacetone;  
hydroxycarboxylic acids, such as tartaric acid, citric acid, gluconic acid, and 5-sulfosalicylic acid;  
polyamines, such as ethylenediamine,  
35 diethylenetriamine, triethylenetetramine, and triaminotriethylamine;  
aminoalcohols, such as triethanolamine and N-(2-hydroxyethyl)ethylenediamine;

- aromatic heterocyclic bases, such as 2,2'-dipyridyl, 2,2'-diimidazole, dipicoline amine and 1,10-phenanthroline; phenols, such as salicylaldehyde, disulfopyrocatechol, and chromotropic acid;
- 5 aminophenols, such as 8-hydroxyquinoline and oxinesulfonic acid;
- oximes, such as dimethylglyoxime and salicylaldoxime; peptides containing proximal chelating functionality such as polycysteine, polyhistidine, polyaspartic acid,
- 10 polyglutamic acid, or combinations of such amino acids; Schiff bases, such as disalicylaldehyde 1,2-propylenediimine;
- tetrapyrroles, such as tetraphenylporphin and phthalocyanine;
- 15 sulfur compounds, such as toluenedithiol, meso-2,3-dimercaptosuccinic acid, dimercaptopropanol, thioglycolic acid, potassium ethyl xanthate, sodium diethyldithiocarbamate, dithizone, diethyl dithiophosphoric acid, and thiourea;
- 20 synthetic macrocyclic compounds, such as dibenzo[18]crown-6, (CH<sub>3</sub>)<sub>6</sub>-[14]-4,11-diene-N<sub>4</sub>, and (2.2.2-cryptate); and
- phosphonic acids, such as nitrilotrimethylenephosphonic acid,
- 25 ethylenediaminetetra(methylenephosphonic acid), and hydroxyethylidenediphosphonic acid, or combinations of two or more of the above agents.
- Preferred residues of chelating agents contain polycarboxylic acid or carboxylate groups and include
- 30 elements present in: ethylenediamine-N,N,N',N'-tetraacetic acid (EDTA); N,N,N',N",N"-diethylenetriaminepentaacetic acid (DTPA); 1,4,7,10-tetraazacyclododecane-N,N',N",N"'-tetraacetic acid (DOTA); 1,4,7,10-tetraazacyclododecane-N,N',N"-triacetic acid (DO3A); 1-oxa-4,7,10-
- 35 triazacyclododecane-N,N',N"-triacetic acid (OTTA); trans(1,2)-cyclohexanodiethylenetriamine pentaacetic acid (CDTPA)







(B4A) ;



(P4A) ;




(TMT) ;



(DCDTPA)

; and



Other suitable residues of chelating agents are described in PCT/US91/08253, the disclosure of which is hereby incorporated by reference. In formula I above, Z is the residue of one or more chelating agents. If Z is the residue of multiple chelating agents, such agents can be linked together by a linking group such as described below.

- The residue of the chelating agent is linked to the poly(alkylene oxide) moiety through a chemical bond or a linking group, i.e., L and L<sub>1</sub> in formula I above. Preferred linking groups include nitrogen atoms in groups such as amino, imido, nitrilo and imino groups; alkylene, preferably containing from 1 to 18 carbon atoms such as methylene, ethylene, propylene, butylene and hexylene, such alkylene optionally being interrupted by 1 or more heteroatoms such as oxygen, nitrogen and sulfur or heteroatom-containing groups;
- carbonyl;
  - sulfonyl;
  - sulfinyl;
  - ether;
  - thioether;
  - ester, i.e., carbonyloxy and oxycarbonyl;
  - thioester, i.e., carbonylthio, thiocarbonyl, thiocarbonyloxy and oxythiocarbonyl;
  - amide, i.e., iminocarbonyl and carbonylimino;
  - thioamide, i.e., iminothiocarbonyl and thiocarbonylimino;
  - thio;
  - dithio;


phosphate;

phosphonate;


urelene;

thiourelene;

- 5 urethane, i.e., iminocarbonyloxy and oxy carbonylimino;  
thiourethane, i.e., iminothiocarbonyloxy, and  
oxythiocarbonylimino;  
an amino acid linkage, i.e., a



- group wherein  $n=1$  and  $\text{X}^1$ ,  $\text{X}^2$  and  $\text{X}^3$  independently are H,  
alkyl, containing from 1 to 18, preferably 1 to 6 carbon  
atoms, such as methyl, ethyl and propyl, such alkyl  
15 optionally being interrupted by 1 or more heteroatoms such  
as oxygen, nitrogen and sulfur, substituted or  
unsubstituted aryl, containing from 6 to 18, preferably 6  
to 10 carbon atoms such as phenyl, hydroxyiodophenyl,  
hydroxyphenyl, fluorophenyl and naphthyl, aralkyl,  
20 preferably containing from 7 to 12 carbon atoms, such as  
benzyl, heterocyclyl, preferably containing from 5 to 7  
nuclear carbon and one or more heteroatoms such as S, N, P  
or O, examples of preferred heterocyclyl groups being  
pyridyl, quinolyl, imidazolyl and thienyl;  
25 heterocyclylalkyl, the heterocyclyl and alkyl portions of  
which preferably are described above;  
or a peptide linkage, i.e., a



- group wherein  $n>1$  and each  $\text{X}^1$ ,  $\text{X}^2$  and  $\text{X}^3$  are  
independently represented by a group as described for  
 $\text{X}^1$ ,  $\text{X}^2$  and  $\text{X}^3$  above. Two or more linking groups can be  
used, such as, for example, alkyleneimino and  
35 iminoalkylene. It is contemplated that other linking


groups may be suitable for use herein, such as linking groups commonly used in protein heterobifunctional and homobifunctional conjugation and crosslinking chemistry. Especially preferred linking groups include

- 5 unsubstituted or substituted imino groups which when linked to the carbonyl in the residue of a chelating agent forms an amide group.

The linking groups can contain various substituents which do not interfere with the  
10 polymerization reaction. The linking groups can also contain substituents which can otherwise interfere with the polymerization reaction, but which during the polymerization reaction, are prevented from so doing with suitable protecting groups commonly known in the  
15 art and which substituents are regenerated after the polymerization by suitable deprotection. The linking groups can also contain substituents that are introduced after the polymerization. For example, the linking group can be substituted with substituents such as  
20 halogen, such as F, Cl, Br or I; an ester group; an amide group; alkyl, preferably containing from 1 to about 18, more preferably, 1 to 4 carbon atoms such as methyl, ethyl, propyl, i-propyl, butyl, and the like; substituted or unsubstituted aryl, preferably containing  
25 from 6 to about 20, more preferably 6 to 10 carbon atoms such as phenyl, naphthyl, hydroxyphenyl, iodophenyl, hydroxyiodophenyl, fluorophenyl and methoxyphenyl; substituted or unsubstituted aralkyl, preferably containing from 7 to about 12 carbon atoms, such as  
30 benzyl and phenylethyl; alkoxy, the alkyl portion of which preferably contains from 1 to 18 carbon atoms as described for alkyl above; alkoxyaralkyl, such as ethoxybenzyl; substituted or unsubstituted heterocyclyl, preferably containing from 5 to 7 nuclear carbon and  
35 heteroatoms such as S, N, P or O, examples of preferred heterocyclyl groups being pyridyl, quinolyl, imidazolyl and thienyl; a carboxyl group; a carboxyalkyl group, the alkyl portion of which preferably contains from 1 to 8

carbon atoms; the residue of a chelating group,  
preferably comprised of elements such as described for Z  
above but being subtended from the backbone at one  
covalent site of such elements; or a poly(alkylene  
oxide) moiety, preferably such as described for Q above  
but being subtended from the backbone of the polymer at  
one site of the poly(alkylene oxide) moiety and  
terminated by substituents selected from, for example,  
H, OH, alkyl, alkoxy, or elements of a chelating agent  
as described above.

In a preferred embodiment L and L<sub>1</sub>  
independently represent



wherein L<sub>2</sub> and L<sub>3</sub> independently represent a chemical  
bond or a linking group such as described above, and R  
and R<sup>1</sup> independently represent H; or a substituent  
attached to the linking group such as described above.

The polymer of the invention can comprise any  
cation or combination of cations. For example, M<sup>(+a)</sup> can  
be H<sup>+</sup>, in which case the polymer is in its nonmetallized  
acid form, or a metal ion such as Li<sup>+</sup>, Na<sup>+</sup>, Al<sup>+3</sup>, K<sup>+</sup>, Ca<sup>+2</sup>,  
Mg<sup>+2</sup>, Cu<sup>+</sup>, Cs<sup>+</sup>, Zn<sup>+2</sup>, Cu<sup>++</sup>, Ag<sup>+</sup> and Sn<sup>++</sup>, or a basic nitrogen  
or phosphorus salt, such as a quaternary ammonium or  
phosphonium salt.

For MR imaging applications, M<sup>(+a)</sup> preferably  
represents a paramagnetic metal ion such as an ion of  
metals of atomic number 21 to 29, 42, 44 and 57 to 71,  
especially 57 to 71. Ions of the following metals are  
preferred: Cr, V, Mn, Fe, Co, Ni, Cu, La, Ce, Pr, Nd, Pm,  
Sm, Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb and Lu. Especially  
preferred are Cr<sup>+3</sup>, Cr<sup>+2</sup>, V<sup>+2</sup>, Mn<sup>+3</sup>, Mn<sup>+2</sup>, Fe<sup>+3</sup>, Fe<sup>+2</sup>, Co<sup>+2</sup>,  
Gd<sup>+3</sup> and Dy<sup>+3</sup>.

For therapeutic and diagnostic imaging  
applications, M can be a radioactive metal ion isotope.  
The radioactive metal ion isotope can be an ion of an  
isotope of a metal selected, for example, from Sc, Fe, Pb,

Ga, Y, Bi, Mn, Cu, Cr, Zn, Ge, Mo, Tc, Ru, In, Sn, Re, Sr, Sm, Lu, Eu, Sb, W, Re, Po, Ta and Tl ions. Preferred isotopes of radioactive metal ions include  $^{44}\text{Sc}$ ,  $^{64,67}\text{Cu}$ ,  $^{111}\text{In}$ ,  $^{212}\text{Pb}$ ,  $^{68}\text{Ga}$ ,  $^{90}\text{Y}$ ,  $^{153}\text{Sm}$ ,  $^{212}\text{Bi}$ ,  $^{99\text{m}}\text{Tc}$  and  $^{188}\text{Re}$ .

5                   E can be one or more counterions. For example, E can be one or more anions, such as a halide, such as chloride and iodide; sulfate; phosphate; nitrate; and acetate. E can be one or more cations such as  $\text{Na}^+$ ,  $\text{K}^+$ , meglumine, and the like. For in vivo applications,  
10 nontoxic physiologically tolerable anions are, of course, desirable.

                  In structure I above, w is 0 or 1, r is 0 or 1, a is an integer preferably from 1 to 4, b is an integer preferably from 0 to 3, and d is an integer preferably from  
15 0 to 4. When E is present, i.e., when w is 1, b most preferably is 1 or 2. d can range up to about 100 when Z comprises the residues of multiple chelating groups. The total positive charge on the cations equals the sum of the total charge on the residue of the chelating group plus the  
20 total charge on any counterions E present, i.e.,  $a=d+b$ .

                  The metal content in the polymer of the invention can be 0, e.g., when  $\text{M}^{+a}=\text{H}^+$ , or it can vary from about 0.9 up to about 30% based on the total weight of the polymer. The metal can be present in an amount of 0.9-30%,  
25 preferably 1-25%, and more preferably 2-20% by weight.

                  The polymer in structure I can be capped at the termini with groups independently selected from Z, Q, L or  $\text{L}_1$  to which is bound a terminal hydrogen atom, OH, alkyl, alkoxy, or elements of a linking group substituent such as  
30 described above. In preferred embodiments, wherein the polymer is a polyamide, the polymer can be capped with groups such as hydrogen or hydroxyl groups or with groups derived from polyamide chain terminating agents such as from monoamines and monoacyl derivatives such as  
35 monoanhydrides, e.g., acetic anhydride, or with groups derived from elements of the residue of a chelating group as defined above. It is further contemplated that cyclic polymers, i.e., non-capped polymers can be prepared.

The molecular weight (MW) of the polymer of this invention can vary widely, i.e., from about 1,000 to  $10^8$  or greater, as measured by gel permeation chromatography (GPC). The polymer can be prepared in water-soluble, 5 water-dispersible or water-insoluble forms, depending on the intended application. Water-soluble polymers generally are of MW from 1,000 to about 250,000. Water-insoluble crosslinked polymers generally are of MW from  $10^5$  to  $10^8$ .

The polymer of this invention can be prepared by 10 contacting a reactive poly(alkylene oxide) species with a chelating agent or precursor thereof containing reactive functionality in a non-reactive solvent to form the polymer. The poly(alkylene oxide) species can be substituted or unsubstituted.

15 The preferred reaction conditions, e.g., temperature, pressure, solvent, etc., depend primarily on the particular reactants selected and can be readily determined by one skilled in the art.

Suitable reactive poly(alkylene oxide) species 20 include terminally functionalized poly(alkylene oxide) diamines, poly(alkylene oxide) dihydrazines, poly(alkylene oxide) diisocyanates, poly(alkylene oxide) diols, poly(alkylene oxide) dialdehydes, poly(alkylene oxide) dicarboxylic acids, poly(alkylene oxide) bis(vinyl 25 sulfonyl) ethers, poly(alkylene oxide) diphosphates, poly(alkylene oxide) N,N-dialkylaminophosphoramidates, poly(alkylene oxide) diepoxides, poly(alkylene oxide) dialkoxides, poly(alkylene oxide) disulfonates, poly(alkylene oxide) dihalides and the like. The above- 30 described poly(alkylene oxide) species are linear difunctional species. Tri- and higher multifunctional branched species relating to the above are also useful.

Suitable chelating agents and precursors thereof containing reactive functionality include polycarboxylic 35 acids in dianhydride form, di(sulfonyl chlorides), di(alkyl sulfates), di(vinyl sulfones), diesters and the like. As will be recognized by one skilled in the art, a suitably blocked progenitor to the chelating agent or precursor

thereof containing reactive functionality can be contacted with the reactive poly(alkylene oxide) moiety to form the polymer, and then the blocking group can be subsequently removed by techniques known in the art. It is contemplated  
5 that additional chelating functional groups can be introduced by suitable chemical modification at the unblocked sites. If hydroxy substituents are to be selectively present in the final polymer, they preferably should be temporarily blocked during polymerization, e.g.,  
10 by conventional blocking techniques, to minimize formation of undesirable byproducts, e.g., polyester-amide derived therefrom. However, for some purposes, polyester-polyamides which contain one or more ester linking groups in the backbone of the polymer are contemplated to be  
15 useful. The use of condensing agents such as carbodiimides is also contemplated to be useful in the formation of the polymers of this invention.

In a preferred embodiment, the polymer of this invention can be prepared by reacting a linear  
20 poly(alkylene oxide) diamine with a precursor of a chelating agent in an internal dianhydride form.

The poly(alkylene oxide) diamine can be prepared by reacting an activated form of the poly(alkylene oxide) with ammonia, a primary amine, a polyamine, an amide, or an  
25 azide followed by reduction. The amino group can be introduced by other methods known in the art. Suitable illustrative amines include N-methylamine, amino acids, aminomethyl pyridine, aminomethylthiophene, methoxyethoxyethylamine, methoxyethylamine and aminobenzoic  
30 acid. Exemplary useful polyamines include diaminoethane, tris(aminoethyl)amine, and diethylenetriamine.

The linear poly(alkylene oxide) in its diol form is widely available commercially or can be prepared by techniques well known to those skilled in the art. The  
35 poly(alkylene oxide) is activated for nucleophilic displacement by reacting it with an activator such as p-toluenesulfonyl chloride, thionyl chloride, thionyl bromide, an alkylsulfonyl chloride, e.g.,  $\text{CH}_3\text{SO}_2\text{Cl}$ , a



sulfonic acid anhydride, or any other suitable activator known in the art. The activated form of the poly(alkylene oxide) thus can be a ditosylate, a dichloride, a dibromide, etc.

5                   The activated form of the poly(alkylene oxide) is reacted preferably with a stoichiometric excess of the amine, in an inert solvent preferably at a temperature, e.g., 100-160°C, and pressure, e.g., 1 to 10 atmospheres, sufficient to drive the reaction to completion. Suitable  
10 solvents include dioxane, ethanol, and other alcohols. Thereafter, the poly(alkylene oxide) diamine preferably is isolated, e.g., by evaporation or precipitation, and purified, e.g., by dissolving in a suitable solvent such as methylene chloride, chloroform or trichloroethane, and then  
15 washing the solution with an excess of aqueous NaOH, or by any other suitable isolation and purification techniques.

                  The internal anhydride forms of the chelating agents described above are commercially available and/or can be prepared by techniques known in the art. For  
20 example, the internal anhydride forms of EDTA and DTPA are commercially available. The internal anhydride forms of DOTA, DO3A, OTTA, B4A, P4A and TMT can be prepared by techniques known in the art. For example, the anhydrides can be prepared by heating the corresponding acids in  
25 acetic anhydride in the presence of pyridine as catalyst. Methods for the preparation of B4A, P4A and TMT are described in U.S. Patent 4,859,777. Mixed anhydrides are also suitable.

                  The reactive polyalkyleneoxide diamine can be  
30 reacted with the internal dianhydride in a non-reactive solvent to form the unmetallized polymer. The reaction conveniently can take place at approximately room temperature and atmospheric pressure. However, higher and lower temperatures and pressures are contemplated.  
35 Suitable solvents include dimethylsulfoxide, dimethylformamide, acetonitrile, chloroform, dichloromethane and 1,2-dichloroethane. The nonmetallized

polymer preferably is isolated and then purified, e.g., by diafiltration.

The metallized polymer can be formed by contacting the unmetallized polymer sequentially or simultaneously with one or more sources of metal ions. This can be conveniently accomplished by adding one or more solutions or one or more metal ion solid salts or metal ion oxides preferably sequentially, to a solution, preferably an aqueous solution, of the polymer. Thereafter or between sequential addition of metal ions, the chelated polymer preferably is diafiltered in water to remove excess unbound metal.

A general reaction scheme for this method of preparing the polymers of this invention and illustrative examples are set forth below.

Alternatively, the polymer can be prepared in a condensation polymerization reaction between a suitable diamine and a diacid containing the metallized chelating group, in a suitably activated form, e.g., in the form of an activated diester.

The molecular weight of the polymer product depends upon many factors including, for example, the molecular weight of the starting poly(alkylene oxide) moiety, the presence or absence of reactive polymerization chain terminating agents (such as monoanhydrides or monoamines in the case of polyamides) which reduce molecular weight by end-capping the polymer during the polymerization process, the absence or presence of reactive crosslinkers or low molecular weight chain extenders which increase the MW of the polymer during polymerization, and the relative concentrations of the poly(alkylene oxide) and chelator moiety present during the polymerization reaction which in turn affects the number of recurring units in the polymer product. To form the polymer of this invention in a water-insoluble form, the above described procedure can be modified to incorporate a crosslinker, e.g., a crosslinkable tri- or higher polyamine, and/or by adding a reactive crosslinking agent, which can be the reactive


chelating moiety, or , e.g., a diacid or higher acid  
chloride, to the polymerization reaction. The preparation  
of insoluble and water-soluble polymers of molecular weight  
1,000 to  $10^8$  can be accomplished by routine experimentation  
5 by one skilled in the art of polymer synthesis techniques.

The following examples further illustrate the  
invention.

Examples 1-12 illustrate the preparation of non-  
10 crosslinked polymers of the invention.

Example 1

A polymer of the invention (Ia) was prepared in  
15 accordance with reaction scheme A as described below.



- A solution of 100.0 g (0.0690 mol) of PEO of average molecular weight (MW) 1450 in toluene (1500 ml) was refluxed for 2 hours with azeotropic removal of water. The solution was cooled to 25°C, then treated with triethylamine (46.1 ml, 0.331 mol), 4-dimethylaminopyridine (1.69 g, 0.0138 mol) and
- 5 *p*-toluenesulfonyl chloride (57.9 g, 0.303 mol), and then heated for 4 days at 60°C under an atmosphere of nitrogen. After cooling to room temperature, the reaction mixture was filtered and the filtrate was extracted twice with water. The combined aqueous extracts were washed with ether, then
- 10 extracted twice with CHCl<sub>3</sub>. The combined CHCl<sub>3</sub> extracts
- 15

were dried over anhydrous magnesium sulfate and then concentrated to yield 121.3 g of product (1).

A solution of 42.2 g (0.0240 mol) of the ditosylate 1 in 420 ml of dioxane was cooled in an ice bath and a stream of methylamine was introduced over a period of 35 minutes. The reaction mixture was then heated in a sealed stainless steel reactor at 160°C for 16 hours, cooled to room temperature, and then filtered. The filtrate was concentrated to remove solvent, then treated with water (844 ml) and 1.0 N NaOH (95.2 ml) and extracted twice with  $\text{CHCl}_3$ . The combined  $\text{CHCl}_3$  extracts were dried over anhydrous magnesium sulfate and concentrated to leave 31.0 g of product (2) ( $\text{R}^2=\text{CH}_3$ ).

A solution of 9.00 g (6.10 mmol) of the bis-(N-methylamine) 2 in 45 ml of dimethylsulfoxide (DMSO) was treated with triethylamine (1.70 ml, 12.2 mmol) and a solution of 2.18 g (6.10 mmol) of diethylenetriaminepentaacetic acid internal dianhydride in DMSO (45 ml). The reaction mixture was stirred at room temperature for 16 hours, then treated with 360 ml of water. The resultant solution was filtered through a 0.45  $\mu\text{m}$  nylon filter and the filtrate was diafiltered against water in a diafiltration cell equipped with a 3000 MW cut-off membrane to leave 170 ml of a solution of (3) ( $\text{R}^2=\text{CH}_3$ ).

A 160 ml portion of the aqueous solution was treated with a two-fold molar excess of gadolinium(III) chloride hexahydrate, and then was diafiltered against water as described above. Lyophilization of the retentate yielded 8.66 g of product (1a) ( $\text{R}^2=\text{CH}_3$ ) of average MW 16,300 daltons (as determined by SEC-HPLC using PEO molecular weight standards). Elemental analysis for  $\text{C}_{82}\text{H}_{156}\text{GdN}_5\text{O}_{40}\cdot 4\text{H}_2\text{O}$ :

	<u>Element</u>	<u>% Theory</u>	<u>% Found</u>
35	C	47.32	47.15
	H	7.94	7.89
	N	3.36	3.30
	Gd	7.55	7.37

The relaxivity ( $T_1$ )<sup>-1</sup> of this material at 20 MHz and 40°C was found to be 6.2 mM<sup>-1</sup>s<sup>-1</sup>.

Intravenous administration of 100, 200 and 400 mg/Kg to mice resulted in no deaths, no effect on body weight and no abnormalities upon necropsy after 14 days.

The same product, but prepared using radioactive <sup>153</sup>Gd, was employed in biodistribution studies in rats to determine a blood-pool half-life (elimination phase) of 75 minutes.

#### Example 2

In a manner similar to Example 1, a polymeric gadolinium chelate (Ia, R<sup>2</sup> = CH<sub>3</sub>) of average MW 8,010 was prepared from PEO of MW 1000. The blood-pool half-life (elimination phase) was determined to be 48 minutes.

#### Example 3

In a manner similar to Example 1, a polymeric gadolinium chelate (Ia, R<sup>2</sup>=CH<sub>3</sub>) of average MW 16,800 was prepared from PEO of average MW 2000.

Example 4

In a manner similar to Example 1, a polymeric gadolinium chelate (**1a**,  $R^2 = CH_3$ ) of average MW 22,400 was prepared from PEO of average MW 3350. Elemental analysis for  $C_{168}H_{328}GdN_5O_{83} \cdot 5H_2O$ :

	<u>Elemental</u>	<u>% Theory</u>	<u>% Found</u>
	C	50.00	50.00
10	H	8.53	8.61
	N	1.75	1.71
	Gd	3.94	3.78

The blood-pool half-life (elimination phase) of this material in rats was determined to be 141 minutes.

Example 5

This example describes the preparation of a polymer (**1a**) wherein  $R^2=H$ .

A solution of 15.30 g (11.70 mmol) of ditosylate **1** prepared from PEO of average MW 1000 in 153 ml of absolute ethanol was cooled in an ice bath, and a stream of ammonia was introduced over a period of 30 minutes. The reaction mixture was heated in a stainless steel reactor at 100°C for 16 hr, cooled to room temperature, and then filtered. The filtrate was concentrated to remove solvent, treated with water (153 ml) and 1.0 N NaOH (46.8 ml), and then extracted twice with  $CHCl_3$ . The  $CHCl_3$  extracts were dried over anhydrous magnesium sulfate, filtered, and then concentrated to leave 12.20 g of product (**2**) ( $R^2=H$ ).

A solution of 11.22 g (11.24 mmol) of the diamine (**2**) in 56 ml of DMSO was treated with triethylamine (3.13 ml, 22.5 mmol) and a solution of 4.017 g (11.24 mmol) of diethylenetriaminepentaacetic acid dianhydride in DMSO (56 ml). The reaction mixture was stirred at room temperature for 16 hr, and then treated with 448 ml of water. The resulting solution was filtered through a 0.45  $\mu m$  filter, and the filtrate was diafiltered against water

in a diafiltration cell equipped with a 3000 MW cut-off membrane to leave 225 ml of solution.

A 208 ml portion of the aqueous solution was treated with a two-fold excess of gadolinium (III) chloride hexahydrate, and then diafiltered against water. Lyophilization of the retentate yielded 11.58 g of product (Ia, R<sup>2</sup>=H) of average MW 12,500. Elemental analysis for C<sub>60</sub>H<sub>112</sub>GdN<sub>5</sub>O<sub>30</sub>·2H<sub>2</sub>O:


Element	%Theory	%Found
C	45.70	45.95
H	7.42	7.53
N	4.44	3.85
Gd	9.97	10.20

#### Example 6

Example 5 was repeated except that the starting PEO had an average MW of 1450. The lyophilized product was determined to have an average MW of 21,900.

#### Example 7

Example 1 was repeated except that B4A-dianhydride was used in place of DTPA-dianhydride. The product (Ib) was determined to have an average MW of 17,600.




Elemental analysis for C<sub>88</sub>H<sub>156</sub>ClGdN<sub>6</sub>O<sub>38</sub>·4H<sub>2</sub>O:



	<u>Element</u>	<u>%Theory</u>	<u>%Found</u>
	C	48.69	48.56
	H	7.61	7.58
5	N	3.87	3.76
	Gd	7.24	7.09

Example 8

10        Example 1 was repeated except that P4A-dianhydride was used in place of DTPA-dianhydride. The product (Ic) was determined to have an average MW of 20,000.



Elemental analysis for  $C_{83}H_{153}ClGdN_5O_{38} \cdot 4H_2O$ :

20	<u>Element</u>	<u>%Theory</u>	<u>%Found</u>
	C	47.61	47.38
	H	7.75	7.96
	N	3.34	3.21
	Gd	7.51	7.46

25

Example 9

Example 1 was repeated except that DyCl<sub>3</sub> was used in place of GdCl<sub>3</sub>. The lyophilized product was found to have an average MW of 14,800. The relaxivity (T<sub>2</sub>)<sup>-1</sup> of this material at 20 MHz and 40°C was found to be 0.109 mM<sup>-1</sup>s<sup>-1</sup>. Elemental analysis for C<sub>82</sub>H<sub>156</sub>DyN<sub>5</sub>O<sub>40</sub>:

	<u>Element</u>	<u>%Theory</u>	<u>%Found</u>
10	C	48.89	48.76
	H	7.80	7.87
	N	3.48	3.48
	Dy	8.07	7.80

15 Example 10

Example 9 was repeated except that the starting PEO had an average MW of 2000. The lyophilized product was found to have an average molecular weight of 15,300. Elemental analysis for C<sub>106</sub>H<sub>204</sub>DyN<sub>5</sub>O<sub>52</sub>·4H<sub>2</sub>O:

	<u>Element</u>	<u>%Theory</u>	<u>%Found</u>
	C	48.46	48.71
	H	8.17	8.05
25	N	2.68	2.52
	Dy	6.21	6.04

Example 11

Example 9 was repeated except that the starting PEO had an average MW of 3350. The lyophilized product was found to have an average molecular weight of 20,100. Elemental analysis for C<sub>168</sub>H<sub>328</sub>DyN<sub>5</sub>O<sub>83</sub>·H<sub>2</sub>O:

35

	<u>Element</u>	<u>%Theory</u>	<u>%Found</u>
	C	51.15	50.93
	H	8.48	8.45
	N	1.78	1.80
5	Dy	4.12	4.05

#### Example 12

Example 5 was repeated except that DyCl<sub>3</sub> was used  
10 in place of GdCl<sub>3</sub>. The lyophilized product was found to  
have an average MW of 45,500. The relaxivity (T<sub>2</sub>)<sup>-1</sup> of  
this material at 20 MHz and 40°C was found to be 0.122 mM<sup>-1</sup>  
s<sup>-1</sup>. Elemental analysis for C<sub>80</sub>H<sub>152</sub>DyN<sub>5</sub>O<sub>40</sub>·4H<sub>2</sub>O:

15	<u>Element</u>	<u>%Theory</u>	<u>%Found</u>
	C	46.68	46.75
	H	7.83	7.69
	N	3.40	3.15
	Dy	7.89	8.04

20

Examples 13-16 illustrate the preparation of  
crosslinked polymers of the invention.

#### Example 13

25

A solution of 15.45 g (8.788 mmol) of ditosylate  
(1) (prepared from PEO of average MW 1450) in 155 ml of  
dioxane was treated with 20.4 g (0.176 mol) of 1,6-  
hexanediamine. The reaction mixture was heated in a  
30 stainless steel reactor at 160°C for 16 hours. The cooled  
reaction mixture was concentrated to remove solvent, and  
then treated with water (309 ml) and 1.0 N NaOH (35.2 ml).  
The aqueous solution was washed twice with ether, and then  
extracted twice with CHCl<sub>3</sub>. The combined CHCl<sub>3</sub> extracts  
35 were dried over anhydrous magnesium sulfate, filtered and  
concentrated at 80°C at 0.5 mm Hg to remove solvent and  
excess 1,6-hexanediamine and to leave 12.63 g of product  
(2) (R<sup>2</sup>=H<sub>2</sub>N(CH<sub>2</sub>)<sub>6</sub>).

A solution of 4.00 g (2.43 mmol) of (2) ( $R^2=H_2N(CH_2)_6$ ) in 44 ml of DMSO was treated with triethylamine (1.35 ml, 9.72 mmol) and a solution of 0.867 g (2.43 mmol) of diethylenetriaminepentaacetic acid dianhydride in DMSO (48 ml). The reaction mixture was stirred at room temperature for 16 hours, and then treated with 384 ml of water. The resulting solution was filtered through a 0.45  $\mu$ m nylon filter and the filtrate was diafiltered against water in a diafiltration cell equipped with a 10,000 MW cut-off membrane.

The retentate aqueous polymer solution was treated with a two-fold excess of gadolinium(III) chloride hexahydrate and then diafiltered against water as described above. Lyophilization yielded 2.10 g of cross-linked product of average MW 49,800 and containing 8.03% Gd by weight.

#### Example 14

In a manner similar to Example 13, a cross-linked polymeric gadolinium chelate of average MW 36,200 containing 9.30% Gd by weight was prepared from a solution of 3.31 g (2.01 mmol) of (2) ( $R^2=-(CH_2)_6NH_2$ ) in 76 ml of DMSO, triethylamine (1.12 ml, 8.04 mmol) and a solution of 1.078 g (3.016 mmol) of diethylenetriaminepentaacetic acid dianhydride in DMSO (79 ml).

#### Example 15

In a manner similar to Example 13, a cross-linked polymeric gadolinium chelate of average MW 95,300 containing 11.30% Gd by weight was prepared from a solution of 3.00 g (1.82 mmol) of (2) ( $R^2=-(CH_2)_6NH_2$ ) in 69 ml of DMSO, triethylamine (1.02 ml, 7.29 mmol) and a solution of 1.303 g (3.645 mmol) of diethylenetriaminepentaacetic acid dianhydride in DMSO (72 ml). The relaxivity ( $T_1$ )<sup>-1</sup> of this material at 20 MHz and 40°C was found to be 8.55 mM<sup>-1</sup>s<sup>-1</sup>.

Example 16

In a manner similar to Example 13, ditosylate  
(1) (prepared from PEO of average MW 1450) was reacted with  
5 tris(2-aminoethyl)amine to yield (2)  
( $R^2 = \text{CH}_2\text{CH}_2\text{N}(\text{CH}_2\text{CH}_2\text{NH}_2)_2$ ).

A cross-linked polymeric gadolinium chelate of  
average MW 41,400 was prepared from a solution of 0.80 g  
(0.47 mmol) of (2) ( $R^2 = \text{CH}_2\text{CH}_2\text{N}(\text{CH}_2\text{CH}_2\text{NH}_2)_2$ ) in 8 ml of DMSO,  
10 triethylamine (0.39 ml, 2.8 mmol) and a solution of 0.34 g  
(0.94 mmol) of diethylenetriaminepentaacetic acid  
dianhydride in DMSO (8 ml). The relaxivity ( $T_1$ )<sup>-1</sup> of this  
material at 20 MHz and 40°C was found to be 10.2 mM<sup>-1</sup>s<sup>-1</sup>.

15


Example 17

In a manner similar to Example 4, a polymeric  
chelate (3,  $R^2 = \text{CH}_3$ ) of average MW 28,900 was prepared from  
PEO of MW 3350. Polymeric yttrium-90 chelate was prepared  
20 by the addition of 1  $\mu\text{Ci}$  <sup>90</sup>YCl<sub>3</sub> per  $\mu\text{g}$  of polymer followed  
by a 10-fold excess of non-radioactive YCl<sub>3</sub>·6H<sub>2</sub>O. The  
radiolabeled polymer was purified using a PD-10 (Pharmacia  
LKB Biotechnology) desalting column. When a PBS solution  
of the radiolabeled chelate was injected into the tail vein  
25 of HT29 tumor bearing nude mice, localization of the  
chelate into the tumor was evidenced.

The invention has been described in detail with  
particular reference to certain preferred embodiments  
30 thereof, but it will be understood that variations and  
modifications can be effected within the spirit and scope  
of the invention.

What is claimed:

1. A polymer comprising units comprising a poly(alkylene oxide) moiety linked to the residue of a chelating agent.
- 5 2. The polymer of claim 1 wherein one or more chelating agents therein has a cation associated therewith.
3. The polymer of claim 1 wherein said polymer  
10 comprises from 2 to 1000 of said units.
4. The polymer of claim 1 wherein said units have the structure



15

wherein:

- Z is the residue of a chelating agent;
- Q is a poly(alkylene oxide) moiety;
- M<sup>(+a)</sup> is one or more cations having a total charge  
20 of +a;
- L and L<sub>1</sub> independently represent a chemical bond or a linking group;
- E<sup>(b)</sup> is one or more counterions having a total charge of b;
- 25 w is 0 or 1;
- r is 0 or 1;
- d is the total charge on the linked residue of the chelating group; and
- a = d+b.

30

5. The polymer of claim 4 wherein Z is the residue of a chelating agent selected from the group consisting

of EDTA, DTPA, DOTA, DO3A, OTTA, CDTPA, B4A, P4A, PheMT, DCDTPA and TMT.


6. The polymer of claim 4 wherein Q is selected from the group consisting of a poly(ethylene oxide) moiety, a poly(propylene oxide) moiety and a poly(ethylene oxide)-co- poly(propylene oxide) moiety of MW 250-10,000.

7. The polymer of claim 4 wherein said cation is H<sup>+</sup>, a metal ion, or a basic nitrogen salt.

8. The polymer of claim 4 wherein said cation is H<sup>+</sup>.

9. The polymer of claim 4 wherein L and L<sub>1</sub> independently represent amino, imido, nitrilo, imino, alkylene, carbonyl, sulfonyl, sulfinyl, ether, thioether, ester, thioester, amide, thioamide, thio, dithio, phosphate, phosphonate, urelene, thiourelene, urethane, thiourethane, an amino acid linkage or a peptide linkage.


10. The polymer of claim 4 wherein L and L<sub>1</sub> independently represent



25

L<sub>2</sub> and L<sub>3</sub> independently represent a chemical bond or a linking group; and R and R<sup>1</sup> independently represent H, OH, alkyl, aryl, halogenated aryl, aralkyl, alkoxy, heterocyclyl, a carboxyl group, an ester group, the residue of a chelating group or a poly(alkylene oxide) moiety.

11. The polymer of claim 1 wherein said units are recurring units having the structure



wherein:

- Z is the residue of a chelating agent;  
 Q is a poly(alkylene oxide) moiety,  
 M<sup>(+a)</sup> is one or more cations having a total  
 charge of +a;  
 L<sub>2</sub> and L<sub>3</sub> independently represent a chemical  
 bond or a linking group;  
 R and R<sup>1</sup> independently are H, OH, alkyl, aryl,  
 halogenated aryl, aralkyl, halogenated aralkyl, alkoxy,  
 heterocyclyl, a carboxyl group, a carboxylate group, an  
 ester group, the residue of a chelating group or a  
 poly(alkylene oxide) moiety;  
 E<sup>(b)</sup> is one or more counterions having a total  
 charge of b;  
 w is 0 or 1;  
 r is 0 or 1;  
 d is the total charge on the residue of the  
 chelating group, and  
 a=d+b.

12. The polymer of claim 11 wherein Z is the residue  
 of B4A, M<sup>(+a)</sup> is H<sup>+</sup>, r is 1, w is 0, L<sub>2</sub> and L<sub>3</sub> represent a  
 chemical bond, Q is a poly(ethylene oxide) moiety of MW  
 250-10,000, and R and R<sup>1</sup> are CH<sub>3</sub>.

13. The polymer of claim 11 wherein Z is the residue  
 of P4A, M<sup>(+a)</sup> is H<sup>+</sup>, r is 1, w is 0, L<sub>2</sub> and L<sub>3</sub> represent a  
 chemical bond, Q is a poly(ethylene oxide) moiety of MW  
 250-10,000, and R and R<sup>1</sup> are CH<sub>3</sub>.



14. The polymer of claim 11 wherein Z is the residue of DTPA,  $M^{(+a)}$  is  $H^+$ , r is 1, w is 0,  $L_2$  and  $L_3$  represent a chemical bond, Q is a poly(ethylene oxide) moiety of MW  
5 250-10,000, and R and  $R^1$  are H or  $CH_3$ .

15. The polymer of claim 11 wherein Z is the residue of B4A,  $M^{(+a)}$  is or  $Gd^{+3}$ ,  $Dy^{+3}$ , or  $Y^{+3}$ ,  $E^b$  is  $Cl^-$ , r is 1, w is 1,  $L_2$  and  $L_3$  represent a chemical bond, Q is a  
10 poly(ethylene oxide) moiety of MW 250-10,000, and R and  $R^1$  are  $CH_3$ .

16. The polymer of claim 11 wherein Z is the residue of P4A,  $M^{(+a)}$  is  $Gd^{+3}$ ,  $Dy^{+3}$ , or  $Y^{+3}$ ,  $E^b$  is  $Cl^-$ , r is 1, w is 1,  $L_2$  and  $L_3$  represent a chemical bond, Q is a  
15 poly(ethylene oxide) moiety of MW 250-10,000, and R and  $R^1$  are  $CH_3$ .

17. The polymer of claim 11 wherein Z is the residue of DTPA,  $M^{(+a)}$  is  $Gd^{+3}$ ,  $Dy^{+3}$ , or  $Y^{+3}$ , r is 1, w is 0,  $L_2$  and  $L_3$  represent a chemical bond, Q is a poly(ethylene oxide) moiety of MW 250-10,000, and R and  $R^1$  are H or  $CH_3$ .  
20

18. A method of preparing a polymer comprising units comprising a poly(alkylene oxide) moiety linked to the residue of a chelating agent, said method comprising the steps of providing a reactive poly(alkylene oxide) species, providing a precursor of a chelating agent containing reactive functionality, and contacting said poly(alkylene oxide) moiety with said precursor in a non-reactive solvent to form said polymer.  
25  
30

19. A method of claim 18 wherein said poly(alkylene oxide) species is poly(alkylene oxide) diamine.  
35

20. The method of claim 18 wherein said precursor is a dianhydride.

21. The method of claim 18 wherein said solvent is dimethylsulfoxide or acetonitrile.

22. The method of claim 18 further comprising the  
5 step of contacting said polymer with a source of metal ions to form a metal ion chelated polymer.

23. The method of claim 22 wherein the poly(alkylene  
oxide) moiety is a poly(ethylene oxide) moiety, the  
10 precursor is a dianhydride, and the metal ions are ions of Y or the elements of the lanthanide group of metals.

# INTERNATIONAL SEARCH REPORT

Intern. Application No  
PCT/US 93/09587

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 5 C08G65/32 A61K49/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 C08G A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO,A,90 01024 (MALLINCKRODT INC.) 8 February 1990  see claim 1; example 1 see page 10, line 17 - line 19 ---	1,2,4-7, 9,11,17, 18
X	CHEMICAL PATENTS INDEX, BASIC ABSTRACTS JOURNAL Section Ch, Week 8825, 17 August 1988 Derwent Publications Ltd., London, GB; Class C88, AN 88-173082 & JP,A,63 112 622 (AGENCY OF IND SCI TECH) 17 May 1988 see abstract  ---  -/--	1,2,4, 6-8

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

14 January 1994

Date of mailing of the international search report

18.02.94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 631 epo nl,  
Fax (+ 31-70) 340-3016

Authorized officer

O'SULLIVAN, T

# INTERNATIONAL SEARCH REPORT

Intern. Application No  
PCT/US 93/09587

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,E,30 885 (RIEDER) 23 March 1982  see claim 1 ---	1,2,4, 10,11, 18,19
X	US,A,4 980 148 (DEAN R.T.) 25 December 1990 see claim 1; example 1 ---	1,2,4
X	US,A,3 562 161 (CASERIO F.F. ET AL) 9 February 1971 see column 5, line 40 - line 58 -----	1,2,4

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 93/09587

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9001024	08-02-90	US-A- 5130120 US-A- 5137711 AU-A- 3988589 EP-A- 0425571 JP-T- 4507084	14-07-92 11-08-92 19-02-90 08-05-91 10-12-92
US-E-30885	23-03-82	NONE	
US-A-4980148	25-12-90	US-A- 5246696	21-09-93
US-A-3562161	09-02-71	NONE	